



Product Data

MAKROLON® SL Sign Matte

Description

MAKROLON®SL Sign Matte polycarbonate sheet is a polished one side, matte one side, clear polycarbonate for sign faces. SL Sign Matte offers the sign fabricator two surface finish options from a single inventory, dependent on surface orientation. It also carries a comprehensive warranty - call for details.

Applications:

Formed or flat signage, polished sign face surface or matte.

Typical Physical Properties

Property	Test Method	Units	MAKROLON
PHYSICAL			
Specific Gravity	ASTM D792	-	1.2
Refractive Index @ 72°F	ASTM D542	-	1.586
Light Transmission, Clear 1/8	ASTM D1003	%	86
Light Transmission, Gray/Bronze	ASTM D1003	%	50
Light Transmission, Dark Gray	ASTM D1003	%	18
Rockwell Hardness	ASTM D785	-	M70/R118
Water Absorption, Equilibrium, 24 hrs	ASTM D570	%	0.15
MECHANICAL			
Tensile Strength, Yield	ASTM D638	psi	9000
Tensile Strength, Ultimate	ASTM D638	psi	9500
Tensile Modulus	ASTM D638	psi	345000
Flexural Strength	ASTM D790	psi	13500
Flexural Modulus	ASTM D790	psi	345000
Compressive Strength	ASTM D695	psi	12500
Compressive Modulus	ASTM D695	psi	345000
Elongation	ASTM D638	%	110
Poisson's Ratio	-	-	0.38
Izod Impact Strength, Notched @ 1/8	ASTM D256	ft-lbs/in	12-16
Izod Impact Strength, Unnotched @ 1/8	ASTM D256	ft-lbs/in	60 (No failure)
Instrumented Impact, 1/8	ASTM D3763	ft-lbs	>45
Shear Strength, @ Yield	ASTM D732	psi	6000
Shear Strength, Ultimate	ASTM D732	psi	10000
Shear Modulus	ASTM D732	psi	114000
THERMAL			
Coefficient of Thermal Expansion	ASTM D696	in/in/F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C177	Btu-in/hr-ft ² -F	1.35
Heat Deflection Temperature, @ 264 psi	ASTM D648	F	270
Heat Deflection Temperature, @ 66 psi	ASTM D648	F	280
Brittle Temperature	ASTM D746	F	-200
Shading Coefficient, Clear 1/8	ASHRAE	-	1.02
Shading Coefficient Gray, Bronze 1/8	ASHRAE	-	0.7
U Value 1/4 (summer gain, winter loss)	-	-	0.90, 0.96

Sheffield Plastics Inc. will not be responsible for the use of this information relative to actual application. Users must make their own determination of its suitability for their specific application. No warranty is made for the fitness of any product, and nothing herein waives any of the seller's conditions of sale.

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109



Product Data

MAKROLON® SL Sign Matte

Typical Physical Properties (continued)			
Property	Test Method	Units	MAKROLON
ELECTRICAL			
Dielectric Constant, @ 10 Hz	ASTM D150	-	2.96
Dielectric Constant, @ 60 Hz	ASTM D150	-	3.17
Volume Resistivity	ASTM D257	Ohm-cm	8.2 x 10 ¹⁶
Dissipation Factor, @ 60 Hz	ASTM D150	-	0.0009
Dissipation Factor, @ 1 MHz	ASTM D150	-	0.01
Arc Resistance	ASTM D495	Seconds	
Stainless Steel Strip Electrode			10-11
Tungsten Electrodes			120
Dielectric Strength, in air, 125 mils	ASTM D149	V/mil	380
FLAMMABILITY			
Horizontal Burn, AEB	ASTM D635	Inches	<1
Ignition Temperature, Self	ASTM D1929	F	1070
Ignition Temperature, Flash	ASTM D1929	F	870
UL 94, Clear @ .060	UL 94	-	V2
UL 94, Clear @ .236	UL 94	-	V0

For additional information
please call the Sheffield
Plastics Customer Service
at: 800-254-1707, or email
us at: info@sheffieldplastics.com

Sheffield Plastics Inc.

A Bayer MaterialScience Company

119 Salisbury Road

Sheffield, MA 01257

800-254-1707

Fax: 800-457-3553

www.sheffieldplastics.com

©Copyright, Sheffield Plastics Inc., 2003 Printed in USA
MAKROLON® is a registered trademark of Bayer Corp.



Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109