



Acculam® Epoxyglas G10/ FR4 Product Data Sheet

Product Description

Acculam® Epoxyglas G10/ FR4, is a laminate sheet comprised of a flame retardant epoxy resin and a woven fiberglass substrate. This grade qualifies to NEMA FR4 and MIL-I-24768/27.

Typical Applications

This material has high mechanical strength and excellent electrical insulating qualities in both dry and humid conditions. These attributes along with good fabricating characteristics allow this grade to be used in a wide variety of electrical and mechanical applications.

Typical Properties

Physical Data

Typical Properties	Typical Value	Units
Specific Gravity/Density	1.85	g/cm ³
Water Absorption -.125"	< .10	%
Temperature Index	140 \ 284	°C \ °F
Rockwell Hardness	110	M scale
Bond Strength	> 2,200 \ 1,000	lbs \ kgs
Flexural Strength-LW-A-.125"	> 65,000 \ 448	PSI \ MPa
Flexural Strength-CW-A-.125"	> 50,000 \ 345	PSI \ MPa
Izod Impact Strength-LW	> 10	ft-lbs/in
Izod Impact Strength-CW	> 8	ft-lbs/in
Compressive Strength-Flatwise	> 60,000 \ 415	PSI \ MPa

Electrical Data

Dielectric Breakdown-A	> 50	kV
Dielectric Breakdown-D48/50	> 50	kV
Permittivity-A	4.8	
Permativity-D24/23	4.8	
Dissipation Factor-A	0.017	
Dissipation Factor-D24/23	0.018	

Accurate provides this data as information only and does not imply any warranty for its use or application.



• 18 Morris Place
Yonkers, NY 10705, USA

• 33 Tech Park Drive
E. Falmouth, MA 02536, USA

001 (914) 476-0700 - phone
001 (914) 476-0533 - facsimile

sales@acculam.com - e-mail

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109