



Acculam® Epoxyglas G11 nonFR Product Data Sheet

Product Description

Acculam® Epoxyglas G11 nonFR -Laminate sheet comprised of heat resistant/halogen free epoxy resin and a woven fiberglass substrate. It qualifies to NEMA G11 and MIL-I-24768/3

Typical Applications

This material exhibits extremely high mechanical strength at elevated temperatures and has good dielectric loss and electric strength properties under both dry and humid conditions. It is resistant to flow, dimensional change, chemicals and has low moisture absorption.

Typical Properties

Physical Data

Typical Properties	Typical Value	Units
Specific Gravity/Density	1.85	g/cm ³
Water Absorption -.125"	< .10	%
Temperature Index	180 \ 356	°C \ °F
Rockwell Hardness	115	M scale
Bond Strength	> 2,200 \ 1,000	lbs \ kgs
Flexural Strength-LW-A	> 75,000 \ 520	PSI \ MPa
Flexural Strength-LW-E-1/150	> 40,000 \ 280	PSI \ MPa
Izod Impact Strength-LW	> 10	ft-lbs/in
Izod Impact Strength-CW	> 8	ft-lbs/in
Compressive Strength-Flatwise	> 65,000 \ 448	PSI \ MPa

Electrical Data

Dielectric Breakdown-A	> 50	kV
Dielectric Breakdown-D48/50	> 50	kV
Permittivity-A	4.8	
Permittivity-D24/23	4.8	
Dissipation Factor-A	0.017	
Dissipation Factor-D24/23	0.018	

Accurate provides this data as information only and does not imply any warranty for its use or application.



•18 Morris Place
Yonkers, NY 10705, USA

• 33 Tech Park Drive
E. Falmouth, MA 02536, USA

001 (914) 476-0700 - phone
001 (914) 476-0533 - facsimile
sales@acculam.com - e-mail

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109