



Acculam® Melaglas G5/ G9 Product Data Sheet

Product Description

Acculam® Melaglas G5/ G9 - Laminate sheet comprised of flame retardant melamine resin and a woven fiberglass glass substrate. It qualifies to NEMA G5/G9 and MIL-I-24768/1/8.

Typical Applications

This material has high strength and excellent arc resistance and electrical insulating properties which allows it to be used as mechanical support in electrical equipment, switchgear, and slot wedges where Class "B" insulation is required.

Typical Properties

Physical Data

Typical Properties	Typical Value	Units
Specific Gravity/Density	1.90	g/cm ³
Water Absorption -.125"	< .70	%
Temperature Index	140 \ 284	°C \ °F
Rockwell Hardness	120	M scale
Bond Strength	> 1700 \ 772	lbs \ kgs
Flexural Strength-LW-A-.125"	> 55,000 \ 380	PSI \ MPa
Flexural Strength-CW-A-.125"	> 38,000 \ 262	PSI \ MPa
Izod Impact Strength-LW	> 10	ft-lbs/in
Izod Impact Strength-CW	> 8	ft-lbs/in
Compressive Strength-Flatwise	> 70,000 \ 483	PSI \ MPa

Electrical Data

Dielectric Breakdown-A	> 60	kV
Dielectric Breakdown-D48/50	> 55	kV
Permittivity-A	< 7.0	
Arc Resistance-A	180	SEC
Dissipation Factor-A	0.017	
Dissipation Factor-D24/23	0.018	

Accurate provides this data as information only and does not imply any warranty for its use or application.



•18 Morris Place
Yonkers, NY 10705, USA

•33 Tech Park Drive
E. Falmouth, MA 02536, USA

001 (914) 476-0700 - phone
001 (914) 476-0533 - facsimile
sales@acculam.com - e-mail

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109