



## Acculam® Phenolfab Canvas C, CE Product Data Sheet

### Product Description

Acculam® Phenolfab C/ CE is a laminate sheet comprised of a phenolic resin binder and woven canvas (cotton) substrate. It qualifies to NEMA C & CE and MIL-I-24768/14/16.

### Typical Applications

This material is characterized by good mechanical properties and toughness. It has higher impact strength than NEMA XX grades. Its good machining qualities, moisture resistance and excellent wear resistance can be used in a wide variety of applications.

### Typical Properties

### Typical Value

### Units

#### Physical Data

Specific Gravity/Density	1.36	g/cm <sup>3</sup>
Water Absorption -.125"	< 1.6	%
Temperature Index	125 \ 257	°C \ °F
Rockwell Hardness	105	M scale
Bond Strength	1800 \ 817	lbs \ kgs
Flexural Strength-LW-A-.125"	> 17,000 \ 117	PSI \ MPa
Flexural Strength-CW-A-.125"	> 16,000 \ 110	PSI \ MPa
Izod Impact Strength-LW	> 1.60	ft-lbs/in
Izod Impact Strength-CW	> 1.40	ft-lbs/in
Compressive Strength-Flatwise	> 39,000 \ 270	PSI \ MPa

#### Electrical Data

Dielectric Breakdown-A	> 35	kV
Dielectric Breakdown-D48/50	> 2.5	kV

Accurate provides this data as information only and does not imply any warranty for its use or application.



•18 Morris Place  
Yonkers, NY 10705, USA  
•33 Tech Park Drive  
E. Falmouth, MA 02536, USA  
001 (914) 476-0700 - phone  
001 (914) 476-0533 - facsimile  
sales@acculam.com - e-mail

Dallas, Texas (Corporate Offices)  
Houston, Texas  
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870  
phone 800-282-4388 / 713-979-0660  
phone 800-457-8623 / 601-825-7919

fax 214-239-3871  
fax 713-979-0664  
fax 601-825-7109