



Acculam® Phenolfab Linen L, LE Product Data Sheet

Product Description

Acculam® Phenolfab L/ LE - Laminate sheet comprised of a phenolic resin and a woven linen (cotton) substrate. This material qualifies to NEMA L/LE and MIL-I-24768/13/15.

Typical Applications

This material's improved moisture resistance and machining characteristics allow its use in a wider range of electrical and structural applications than paper grades. Its finer weave fabric also allows for finer machined details & thinner sheets than grades C and CE.

Typical Properties

Physical Data

Typical Properties	Typical Value	Units
Specific Gravity/Density	1.35	g/cm ³
Water Absorption -.125"	< 1.30	%
Temperature Index	125 \ 257	°C \ °F
Rockwell Hardness	105	M scale
Bond Strength	1600 \ 843	lbs \ kgs
Flexural Strength-LW-A-.125"	> 16,500 \ 114	PSI \ MPa
Flexural Strength-CW-A-.125"	> 14,500 \ 100	PSI \ MPa
Izod Impact Strength-LW	> 1.25	ft-lbs/in
Izod Impact Strength-CW	> 1.00	ft-lbs/in
Compressive Strength-Flatwise	> 37,000 \ 255	PSI \ MPa

Electrical Data

Dielectric Breakdown-A	> 40	kV
Dielectric Breakdown-D48/50	> 3.0	kV
Permittivity-A	< 5.80	
Permittivity-D24/23	< 6.00	
Dissipation Factor-A	< .055	
Dissipation Factor-D24/23	< .070	

Accurate provides this data as information only and does not imply any warranty for its use or application.



• 18 Morris Place
Yonkers, NY 10705, USA

• 33 Tech Park Drive
E. Falmouth, MA 02536, USA

001 (914) 476-0700 - phone
001 (914) 476-0533 - facsimile
sales@acculam.com - e-mail

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109