



Acculam® Phenolkraft Paper XX, XXX Product Data Sheet

Product Description

Acculam® Phenolkraft XX/ XXX - Laminate sheet comprised of a phenolic resin and a high alpha saturating paper substrate. It qualifies to NEMA XX/XXX and MIL-I-24768/10/11.

Typical Applications

This material has excellent machining characteristics, low moisture absorption and excellent dimensional stability. It is used in switchgear, relay spacers, power transformer insulating applications as well as numerous mechanical areas.

Typical Properties

Physical Data

Typical Properties	Typical Value	Units
Specific Gravity/Density	1.34	g/cm ³
Water Absorption -.125"	< .90	%
Temperature Index	140 \ 284	°C \ °F
Rockwell Hardness	110	M scale
Bond Strength	> 950 \ 431	lbs \ kgs
Flexural Strength-LW-A-.125"	> 15,000 \ 103	PSI \ MPa
Flexural Strength-CW-A-.125"	> 14,000 \ 97	PSI \ MPa
Izod Impact Strength-LW	> .40	ft-lbs/in
Izod Impact Strength-CW	> .35	ft-lbs/in
Compressive Strength-Flatwise	> 32,000 \ 221	PSI \ MPa

Electrical Data

Dielectric Breakdown-A	> 50	kV
Dielectric Breakdown-D48/50	> 6.0	kV
Permittivity-A	< 5.30	
Permittivity-D24/23	< 5.70	
Dissipation Factor-A	< .038	
Dissipation Factor-D24/23	< .045	

Accurate provides this data as information only and does not imply any warranty for its use or application.



•18 Morris Place
Yonkers, NY 10705, USA

•33 Tech Park Drive
E. Falmouth, MA 02536, USA

001 (914) 476-0700 - phone
001 (914) 476-0533 - facsimile
sales@acculam.com - e-mail

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109