



## Product Data

### MAKROLON® WG

#### Window Grade

MAKROLON® WG polycarbonate engineering plate is an amorphous thermo-plastic sheet. It offers extremely high impact strength, high modulus of elasticity, outstanding dimensional stability and good mechanical and electrical properties. MAKROLON WG demonstrates low levels of black specks or other impurities.

#### Applications

Sight windows for tanks/vessels, viewport windows, medical parts and military applications

Typical Properties			
Property	Test Method	Units	Values
<b>PHYSICAL</b>			
Specific Gravity	ASTM D792	-	1.2
Water Absorption, 24 hrs	ASTM D570	%	0.15
Poisson's Ratio	ASTM E132	-	0.38
<b>MECHANICAL</b>			
Tensile Strength, Ultimate	ASTM D638	psi	9,500
Tensile Strength, Yield	ASTM D638	psi	9,000
Tensile Modulus	ASTM D638	psi	340,000
Elongation	ASTM D638	%	110
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Shear Strength @ Yield	ASTM D732	psi	6,000
Shear Strength, Ultimate	ASTM D732	psi	10,000
Shear Modulus	ASTM D732	psi	114,000
Rockwell Hardness-	ASTM D785	-	M70/R118
<b>THERMAL</b>			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 <sup>-5</sup>
Coefficient of Thermal Conductivity	ASTM C177	BTU·in/hr·ft <sup>2</sup> ·°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D648	°F	280
Brittleness Temperature	ASTM D746	°F	-200
<b>ELECTRICAL</b>			
Dielectric Constant, @10Hz	ASTM D150	-	2.96
Dielectric Constant @ 60Hz	ASTM D150	-	3.17
Volume Resistivity	ASTM D257	Ohm·cm	8.2 x 10 <sup>16</sup>
Dissipation Factor @ 60 Hz	ASTM D150	-	0
Dielectric Strength, in air @ 0.125"	ASTM D149	V/mil	380
<b>OPTICAL</b>			
Haze	D1746	%	1.0
<b>FLAMMABILITY</b>			
UL 94 @ 0.75"-2.00"	UL94	-	VO

Dallas, Texas (Corporate Offices)  
Houston, Texas  
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870  
phone 800-282-4388 / 713-979-0660  
phone 800-457-8623 / 601-825-7919

fax 214-239-3871  
fax 713-979-0664  
fax 601-825-7109



## Product Data

### MAKROLON® WG

#### Fabrication Guidelines

**Cutting:** A circular saw blade with carbide teeth utilizing the "triple chip" tooth design is the preferred method of cutting MAKROLON WG polycarbonate sheet. Table or overhead panel saws are normally used. Circular saws should be run in the speed range of 6000-8000 ft/min. Blades for cutting 3/32" and thicker material should have 3-5 teeth per inch. The hook or rake angle should be 10°-15°.

#### Cautions

The following are suggested guidelines or concerns regarding machining, working with MAKROLON WG polycarbonate sheet or any other engineering plastics.

1. Thermal expansion is up to 10 times greater with plastics than metals.
2. Plastics will lose heat more slowly than metals
3. Avoid localized overheating.
4. Softening/melting temperatures of plastics are much lower than metals.

#### Disclaimer

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.



MAKWG 0410

## Sheffield Plastics

A Bayer MaterialScience LLC Business

119 Salisbury Road  
Sheffield, MA 01257  
800-254-1707

Fax: 800-457-3553

Web site: [www.sheffieldplastics.com](http://www.sheffieldplastics.com)

E-mail: [info@sheffieldplastics.com](mailto:info@sheffieldplastics.com)

©Copyright, 2010

Bayer, the Bayer Cross and MAKROLON® is a registered trademarks of Bayer Corporation.

Dallas, Texas (Corporate Offices)  
Houston, Texas  
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870  
phone 800-282-4388 / 713-979-0660  
phone 800-457-8623 / 601-825-7919

fax 214-239-3871  
fax 713-979-0664  
fax 601-825-7109