



PHYSICAL PROPERTIES

KING STARBOARD[®] XL

CELLULAR MARINE GRADE POLYMER SHEET

Tolerances

Gauges	Width/Length
1/4" - 3/4" ± 5%	Plus Only

Property	Units	ASTM	Nominal Value*
Tensile Strength @ Yield	P.S.I.	D638	>3,300
Flexural Modulus	P.S.I.	D790	130,000
Screw Holding Strength	LBS.	D1761	325
7 Day Water Absorption	%	D570	.09
Weight	LBS./cubic inch		.024

* All values are determined on specimens prepared according to ASTM D 4976. Nominal values should not be interpreted as specifications.

KING STARBOARD[®] XL is made entirely from FDA & USDA Approved materials.



KING PLASTIC CORPORATION

Phone: (941) 493 - 5502 | Fax: (941) 497 - 3274

1100 North Toledo Blade Blvd. North Port, Florida 34288

Web: www.kingplastic.com | www.kingstarboard.com

King Plastic Corporation (KPC) makes no representations or warranties and there are no conditions with respect to accuracy, reliability, or application of the information herein, its products or the safety or suitability thereof, or results obtained, whether expressed or implied including, without limitation, any implied warranty of merchantability of fitness for a particular purpose. Buyers and users must determine the results to be obtained from the application of the information herein and the safety and suitability of KPC's products for their own purposes and assume all risk, responsibility, and liability for all injuries, losses, or damages arising from the application of the information herein or use of KPC's products, whether or not occasioned by KPC's negligence or based on strict product liability. KPC neither assumes nor authorizes any person to assume for it any liability in connection with the use of the information herein or its products.

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109