



PHYSICAL PROPERTIES

POLYPROPYLENE

SHEETS, SLABS AND MASSIVE SHAPES

Tolerances

Gauges	Width/Length
1/8" - 1" +/- 5% (K-STRAIN) 1" +/-10% (COMPRESSION MOLDED)	Plus Only

Property	Units	ASTM	Nominal Value*
Density	g/cc	D1505	0.905
Tensile Strength @ Yield	p.s.i.	D638	>5,400
Elongation @ Yield	%	D638	9.0
Flexural Modulus	p.s.i.	D790	270,000
Durometer	Shore D	D785	42
Vicat Softening Temp.	°C	D1525	89
Notched Izod Impact	ft. lbs./in.	D256	1.3
Heat Deflection Temperature at 66 P.S.I.	°F	D648	203

King Polypropylene meets the standards established by FDA Reg. 21 CFR 177.1520 for all food contact applications.

*All values are determined on specimens prepared according to ASTM testing procedures (if applicable). Nominal values should not be interpreted as specifications.



KING PLASTIC CORPORATION

Phone: (941) 493 - 5502 | Fax: (941) 497 - 3274

1100 North Toledo Blade Blvd. North Port, Florida 34288

Web: www.kingplastic.com | www.kingstarboard.com

King Plastic Corporation (KPC) makes no representations or warranties and there are no conditions with respect to accuracy, reliability, or application of the information herein, its products or the safety or suitability thereof, or results obtained, whether expressed or implied including, without limitation, any implied warranty of merchantability of fitness for a particular purpose. Buyers and users must determine the results to be obtained from the application of the information herein and the safety and suitability of KPC's products for their own purposes and assume all risk, responsibility, and liability for all injuries, losses, or damages arising from the application of the information herein or use of KPC's products, whether or not occasioned by KPC's negligence or based on strict product liability. KPC neither assumes nor authorizes any person to assume for it any liability in connection with the use of the information herein or its products.

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109