



Data Sheet No: 10507
Revision: 00
Effective Date: 7/14/06
Page 1 of 1

DATA SHEET			
PROTEUS® Black Co-Polymer Polypropylene			
Property	Units	Test Method	Typical Average Values
Mechanical			
Specific Gravity, 73° F	-	ASTM D792	.90
Yield Point, 73° F	psi	ASTM D638	3400
Elongation at Yield	%	ASTM D638	11
Tensile Break, 73°F	psi	ASTM D638	4800
Tensile Elongation (at break), 73° F	%	ASTM D638	300
Tensile Modulus of Elasticity, 73° F	psi	ASTM D638	152000
Flexural Modulus of Elasticity, 73° F	psi	ASTM D790	184000
Hardness, Durometer, Shore "D" Scale, 73° F	-	ASTM D2240	73
Izod Impact (notched), 73° F	ft.lb./in.	ASTM D256 Type "A"	8
Thermal			
Heat Deflection Temperature 66 psi	°F	ASTM D648	212
Melting Point (crystalline) peak	°F	ASTM D3418	305
Continuous Service Temperature in Air (Max.)(1)	°F	-	180
Electrical			
Surface Resistivity	Ohms	ASTM D257	>10 ¹⁵
Volume Resistivity	Ohm-cm	ASTM D257	>10 ¹⁵
Flammability @ 3.1 mm (1/8 in.) (3)	-	UL94	HB
Miscellaneous			
Water Absorption	% by wt.	ASTM D570(2)	

- (1) Data represent Quadrant's estimated maximum long-term service temperature based on practical field experience.
- (2) Specimens: 1/8" thick x 2" diameter or square.
- (3) **Estimated rating based on available data.** The UL 94 Test is a laboratory test and does not relate to actual fire hazard. Contact Quadrant for specific UL "Yellow Card" recognition number.

QUADRANT EPP USA, Inc. • 2120 Fairmont Avenue • P.O. Box 14235 • Reading, PA 19612-4235
Tel: (610) 320-6660 • Fax: (610) 320-6866

Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109