



Technical Data Sheet

Harkness Industries MP 950

Polyurethane Composition

MP 950 is a high performance polyether based urethane formulated to give an excellent balance of properties including; tear and abrasion resistance, low heat build-up, good resilience, hydrolysis resistance, and hardness stability. MP 950 may be selected for a wide variety of applications including springs, scraper blades, material handling equipment, rolls, shock absorbers, bumpers, chute liners, wheels, tires, and many more.

Physical Properties

Shore A Hardness	95 +/- 5
100% Modulus, psi (Mpa)	1800 (12.4)
300% Modulus, psi (Mpa)	4000 (27.6)
Tensile, psi (Mpa)	5500 (37.9)
Elongation, %	320%
Tear Strength, Split (ASTM D-470) pli, (kN/m)	150 (26.2)
Tear Strength, Die C (ASTM D-624) pli, (kN/m)	450 (78.3)
Bashore Rebound, %	40
Compression Set %	40
22 hours @ 158°F (70°C), Method B	
Bell Brittle Point, °F (°C)	- 80 (-63)
Abrasion Resistance, NBS Index	300
Specific Gravity	1.14



50 Grandview Court
Cheshire, CT. 06410

Phone: 203-272-3219
Fax: 203-272-0428
Website: www.harknessindustries.com



Dallas, Texas (Corporate Offices)
Houston, Texas
Brandon, Mississippi

phone 800-782-1836 / 214-239-3870
phone 800-282-4388 / 713-979-0660
phone 800-457-8623 / 601-825-7919

fax 214-239-3871
fax 713-979-0664
fax 601-825-7109